



TERMO[®]
SCRIPT

Termoscript KPH AF 48 AM

Thermal paper for receipts, tickets and access controls.

Thermal paper for receipts, tickets and access controls.



TECHNICAL SPECIFICATION | SPECIFICACIÓN TÉCNICA




Paper Features | Características del Papel

Grammage	Thickness	Bekk Smoothness thermal side	Óptical Density Zebra Stripe S600	Image Durability	Sensivity	Paper Color
Gramaje	Calibre	Lisura Bekk cara estucada	Densidad Óptica Zebra Stripe S600	Durabilidad de la imagen	Sensibilidad	Color del Papel
48±1,9	50±5	Min. 300	Min. 1,15	10		
Subtitle Subtítulo Standard Estándar Medium Media High Alto						

Image Stability | Estabilidad de la imagen

Temperature - 24h Temperatura - 24h		> 90%
Moisture (40° - 90%u.r - 24h) Humedad (40° - 90%u.r - 24h)		> 85%
Fluorescent Light - 24h Luz Fluorescente - 24h		> 95%
Sunlight - 5h Luz Solar - 5h		> 90%

Dynamic Sensivity | Sensibilidad Dinámica



*Conditions: The paper should be well sensitized, stored at 20°, 60% RH. Not exposed to ultraviolet or fluorescent light. Do not contact with chemicals or plastics materials.
*Condiciones: El papel debe estar bien sensibilizado, almacenado a 20°, 60% de HR. No expuesto a luz ultravioleta o fluorescente. No entrar en contacto con productos químicos o materiales plásticos.